



JINBO®
金博树脂
Jinbo Resin

浙江大学化学系涂料研究室
Coatings Research Laboratory, Department of Chemistry, Zhejiang University
地址: 浙江大学玉泉校区教八-418室

黄山金质丽科技有限公司
Huangshan Goldenly Technology Co., Ltd.
地址: 黄山歙县循环经济园区
ADD: Shexian Eco-industrial Park, Huangshan, Anhui
电话/TEL: 0559-6661886
传真/FAX: 0559-6661886

浙江金质丽化工有限公司
Zhejiang Goldenly Chemical Co., Ltd.
地址: 浙江省临安市经济开发区
ADD: Lin'an Economic Development Zone ,Hangzhou ,Zhejiang
电话/TEL: 0571-63819416
传真/FAX: 0571-63819416
销售热线: 13336060100 联系人: 郑新凯

重庆办事处
联系人: 陈纪兴
电 话: 023-68857828 13883523800

广东办事处
联系人: 赵 平
电 话: 0760-22267159 13326932598

山东办事处
联系人: 郑广英
电 话: 18615318848

江苏常州办事处
联系人: 蒋达明
电 话: 13775238116



浙江大学化学系涂料研究室
Coatings Research Laboratory, Department of Chemistry, Zhejiang University

黄山金质丽科技有限公司
Huangshan Goldenly Technology Co., Ltd.

浙江金质丽化工有限公司
Zhejiang Goldenly Chemical Co., Ltd.

黄山金质丽科技有限公司 简介

黄山金质丽科技有限公司位于安徽黄山歙县循环园区，占地33000平方米，生产能力为3万吨。公司的前身为杭州金博化工有限公司，成立于1995年，在国内起步较早，专业生产各类丙烯酸树脂。化工出版社出版的《涂料工艺》（第四版）和《涂料制造技术》中的丙烯酸树脂章节为公司技术部编写。

目前公司生产的丙烯酸树脂被广泛地用在飞机、汽车、工程车辆、摩托车、通讯铁塔、防腐防锈、塑胶、机床设备、地坪、建筑、汽车修补等领域的涂料产品，深受客户的好评。

公司与浙江大学化学系长期合作，共同开展涂料新技术、新产品、新工艺的研究，提高涂料的各种性能，以不断满足客户的各种需求，保持公司的市场竞争优势。

公司的目标是全方位打造丙烯酸树脂精品，与涂料行业携手共进，共创美好的明天。

About Us

HuangShan Goldenly Technology Company is located in the Eco-industrial Park, Shexian, HuangShan. Established in 1995, we mainly manufactures acrylic resin, alkyd resin, polyester, and polyurethane curing reagents, with an annual production capacity of 30,000 tons. "JINBO" and "CARLORFUL" are the registered trademarks. The acrylic resin developed by our company has been well received by our customers and widely used in planes, cars, motorcycles, communication towers, floors, buildings, etc.

Our company has been working with the Department of Chemistry at Zhejiang University since 1995 to develop novel technologies, formulas, and protocols in paint products. We have also established sales centers in Zhejiang, Chongqing, Jiangsu, Guangdong, Shandong, and other places.

Our mission: Manufacture high-quality acrylic resin and create a better future for our customers.



厂区大门



厂区一角



生产设备一角



生产设备一角

浙江大学化学系涂料研究室 简介

浙江大学化学系涂料研究室座落在浙大玉泉校区化学系，有教授、博导、博士等各类研究人员十多名，承担多项国家、省部委及各类企业涂料高新科研项目，并拥有浙江金质丽化工有限公司、杭州金质丽科技有限公司、黄山金质丽科技有限公司三大生产基地，从科研到生产取得了多项重大研究成果。1995年12月浙大化学系研制的《聚酯改性丙烯酸树脂》通过浙江省科技厅鉴定。2005年8月，由浙大化学系和浙江金质丽化工有限公司共同研制的《直升机用高固体丙烯酸聚氨酯面漆及配套底漆、抗静电涂料》通过浙江省科技厅鉴定。2007年5月，由浙大化学系和浙江金质丽化工有限公司共同研制的《保温弹性涂料》通过浙江大学技术鉴定。2008年5月由浙江大学和浙江金质丽化工有限公司共同申请的《直升机蒙皮涂料用氟改性丙烯酸树脂制造方法》获国家发明专利。2010年10月与浙江金质丽化工有限公司合作完成《WB-101航空用有机玻璃保护涂料研制》的军工项目并通过鉴定。

About Us

The Coatings Research Laboratory is located in the Department of Chemistry at Zhejiang University. We have dozens of researchers consisting of full professors, leading experts, and PhD candidates. Our laboratory have been undertaking a variety of research projects sponsored by national, provincial, and industrial programs. Our laboratory has a capability of manufacturing a wide range of products including resins, paints, waterborne industrial coatings, architectural coatings, and powder coatings.

► 主要研究人员




蔡国强 男，1959年11月出生，博士，浙大化学系副教授，现任浙江大学化学系涂料研究室主任。



朱龙观 男，1964年5月出生，博士，浙大化学系教授，博士生导师，涂料研究室核心成员。



厉刚 男，1971年10月出生，日本早稻田大学工学博士、博士后，浙江大学化学系副教授，涂料研究室核心成员。



蔡镭 男，1986年8月出生，美国田纳西大学高分子化学博士，现在斯坦福大学从事博士后研究工作。

羟基丙烯酸树脂 Hydroxyl acrylic resin

金博树脂

型号 Product	外观 Appearance	色泽 (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa · s viscosity (1)Gardner (2)mPa · s(25°C)	酸价 Acidity (mgKOH/g)	羟基含量 OH content (100%)	溶剂 Solvent	主要性能 Features	主要用途 Main application
U3018	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	二甲苯/PMA XYL/PMA	丰满度、耐黄变性、耐候性、干性、流平性等性能优越； Good film build, gross, durable, yellowing resistance, drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clearcoat for car
U3025	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐黄变性、耐候性、干性、流平性等性能优越； Good film build, durable, yellowing resistance, good drying, levelling	汽车、轿车面漆、清漆； Topcoat or clearcoat for car
U3025B	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	醋酸丁酯 BAC	无苯溶剂，丰满度、耐黄变性、耐候性、干性等性能优越； Benzene-free, film build, durable, yellowing resistance, drying, levelling	汽车、轿车面漆、清漆； Topcoat or clearcoat for car
U3040	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐黄变性、耐候性、干性、流平性等性能优越，经济型； Film build, durable, yellowing resistance, drying, levelling, economy grade	汽车、轿车、防腐、修车修补、 各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive repair, anticorrosive and industrial field
U3060	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	耐黄变性、耐候性、干性、流平性等性能优越，经济型； Durable, yellowing resistance, drying, levelling, economy grade	汽车、轿车、防腐、修车修补、 各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive repair, anticorrosive and industrial field
U3090K	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	5~9	3.0%	二甲苯/醋酸丁酯 XYL/BAC	快干、耐黄变性、耐候性、干性、流平性等性能优越； Fast drying, durable, yellowing resistance, levelling	汽车快修清漆；Fast drying clearcoat for automotive refinish
U3125	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐黄变性、耐候性、鲜映性等性能优越； Film built, weathering resistance, yellowing resistance, good drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clearcoat for car
U4025A	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	4.3%	二甲苯/PMA XYL/PMA	高羟基、丰满度、耐侯性、耐黄变、干性优越； High OH content, film built, weathering resistance, yellowing resistance, good drying, levelling	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4025C	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	4.3%	二甲苯/PMA XYL/PMA	丰满度、硬度、耐侯性、耐黄变、干性优越； High OH content, film build, weathering resistance, yellowing resistance, drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4035	清澈透明 crystal clear	≤1	70±2	34(Z)~91(Z4) 2300~6200	5~9	4.3%	醋酸丁酯 BAC	无苯溶剂，丰满度、耐侯性、耐黄变、干性优越； Benzene-free, high OH content, Film build, weathering resistance, yellowing resistance, drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4040	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	4.3%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐侯性、耐黄变优越，性价比高； High OH content, Film build, weathering resistance, yellowing resistance, drying, economic grade	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4060	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	5~9	4.3%	二甲苯/醋酸丁酯 XYL/BAC	耐侯性、耐黄变性优越，性价比高； High OH content, weathering resistance, yellowing resistance, drying, economic grade	汽车、轿车、防腐、修车修补、各类 机床等面漆、清漆；Topcoat or clearcoat for car, automotive refinish anticorrosive and industrial field
U4090K	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	6~11	4.0%	二甲苯/醋酸丁酯 XYL/BAC	快干、耐黄变性、耐候性、干性、流平性等性能优越； Fast drying, durable, yellowing resistance, levelling	汽车快修清漆；Fast drying clearcoat for automotive repair
U4240	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	4.3%	二甲苯/PMA XYL/PMA	硬度高、鲜映性、光泽、耐侯性、耐黄变性、流平性优越； High OH content, hardness, built, weathering resistance, yellowing resistance, drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4543	清澈透明 crystal clear	≤1	75±2	50(Z2)~140(Z5) 3400~9900	5~9	4.3%	二甲苯/PMA XYL/PMA	丰满度、耐黄变性、耐候性、鲜映性等性能优越；High OH content, good film built, weathering resistance, yellowing resistance, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clear coat for car

羟基丙烯酸树脂 Hydroxyl acrylic resin

JINBO®

型号 Product	外观 Appearance	色泽 (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa · s viscosity (1)Gardner (2)mPa · s(25°C)	酸价 Acidity (mgKOH/g)	羟基含量 OH content (100%)	溶剂 Solvent	主要性能 Features	主要用途 Main application
U5003	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	甲苯/醋酸丁酯 TOL/BAC	耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Good alcohol resistance, compatibility with CAB381, aluminium orientation, adhesion in ABS plastic, inter-layer adhesion with top clear.	塑胶漆； Plastic coat
U5003B	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	醋酸丁酯 BAC	无苯溶剂，耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Benzene-free, good alcohol resistance, compatibility with CAB381, aluminium orientation, adhesion in ABS plastic, inter-layer adhesion with top clear.	塑胶漆； Plastic coat
U5018	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	甲苯/醋酸丁酯 TOL/BAC	耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Good alcohol resistance, compatibility with CAB381, aluminium orientation, weathering resistance, yellowing resistance, adhesion in ABS plastic, inter-layer adhesion with top PU clear coating.	塑胶漆； Plastic coat
U5020	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	醋酸丁酯/醋酸仲丁酯 BAC/SBAC	无苯溶剂，耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Benzene-free, good alcohol resistance, compatibility with CAB381, aluminium orientation, weathering resistance, yellowing resistance, adhesion in ABS plastic, inter-layer adhesion to top PU&UV clear coating.	塑胶漆； Plastic coat
U5020A	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	二甲苯/醋酸丁酯 XYL/BAC	耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Good alcohol resistance, compatibility with CAB381, aluminium orientation, weathering resistance, yellowing resistance, adhesion in ABS plastic, inter-layer adhesion to top PU&UV clear coating.	塑胶漆； Plastic coat
U5112	清澈透明 crystal clear	≤1	50±2	16(W)~40(Z1) 1100~2700	2~5	1.8%	二甲苯/PMA XYL/PMA	低气味，与CAB互溶，铝粉定位性好，耐候性好；Low odor, compatibility with CAB, aluminium orientation, adhesion in ABS plastic, inter-layer adhesion with top PU&UV clear coating.	塑胶漆、外墙漆； Plastic coat, exterior wall coat
U6020	清澈透明 crystal clear	≤1	60±2	19(X)~50(Z2) 1300~3400	5~9	2.8%	二甲苯 XYL	通用PU树脂； Standard for industrial coating. Economy grade	工业漆； Industrial coat
U6025	清澈透明 crystal clear	≤1	60±2	16(W)~40(Z1) 1100~2700	4~8	2.1%	二甲苯/醋酸丁酯 XYL/BAC	和CAB381-0.5 混溶性好，附着力好，耐候性优，铝粉定位性好；Compatibility with CAB, durable, non yellowing	汽车中涂、底漆、一般工业漆； Primer for car and industrial field
U6026A	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	5~9	2.6%	二甲苯/PMA XYL/PMA	颜料润湿及分散性好，耐候性佳、和CAB相溶性好；Pigment wetting, compatibility with CAB, durable, yellowing resistance	汽车修补1K/2K通用色母，汽车面漆； 1K/2K solid color for automotive refinish
U6027	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	5~9	2.7%	二甲苯/PMA XYL/PMA	颜料润湿及分散性； Pigment wetting, general performance	修补漆2K通用色母； 2K solid color for automotive refinish
U6028	清澈透明 crystal clear	≤1	60±2	91(Z4)~220(Z6) 6200~15000	6~11	2.8%	二甲苯/醋酸丁酯 XYL/BAC	在金属底材上附着力好，耐原子灰中的苯乙烯溶解； Adhesion to metal, resistanc to styrene in putty	需要快速批刮原子灰的金属底漆； Metal primer on which putty is needed to cover in short time
U6034	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	5~9	3.4%	二甲苯/PMA XYL/PMA	颜料润湿及分散性； Pigment wetting, general performance	修补漆2K通用色母； 2K solid color for automotive refinish
U6040	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	5~9	2.6%	二甲苯/PMA/100# XYL/PMA/S-100	耐候性、耐酸碱、耐溶剂、耐水； Durable, chemical resistance	工程防腐、工业等面漆； Anticorrosive and industrial coat
U6045	清澈透明 crystal clear	≤1	60±2	19(X)~50(Z2) 1300~3400	5~9	2.8%	二甲苯/PMA/100# XYL/PMA/S-100	光泽、耐候性、流平性、鲜映性好；Gloss, durable, leveling, distinctness of image is good	汽车面漆；Solid color topcoat for automobile
U6063	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	2~5	1.8%	甲苯/醋酸丁酯 TOL/BAC	耐醇性好，和CAB互溶，铝粉定位性好，适用于塑料一道面漆；Good alcohol resistance, compatibility with CAB, aluminium orientation, weathering resistance, yellowing resistance, adhesion in ABS plastic	塑胶漆 Plastic coat

羟基丙烯酸树脂 Hydroxyl acrylic resin

金博树脂

型号 Product	外观 Appearance	色泽 Color (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa·s viscosity (1)Gardner (2)mPa·s(25℃)	酸价 Acidity (mgKOH/g)	羟基含量 OH content (100%)	溶剂 Solvent	主要性能 Features	主要用途 Main application
U6526	清澈透明 crystal clear	≤1	65±2	34(Z)~91(Z4) 2300~6200	5~9	2.6%	二甲苯/醋酸丁酯/仲丁酯 XYL/BAC/SBAC	通用树脂；性价比高、综合性能良好； Standard for industrial coating, Economy grade for PU resin	可用于防腐、工程机械、机床设备、地坪领域等面漆； Coat for anticorrosive, industrial and floor field
U7010A	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	4~8	2.6%	二甲苯 XYL	通用树脂；性价比高、综合性能良好； Standard for industrial coating, Economy grade for PU resin	一般工业漆； Industrial coat
U7012A	清澈透明 crystal clear	≤1	70±2	91(Z4)~220(Z6) 6200~15000	4~8	2.4%	二甲苯/PMA/醋酸丁酯 XYL/PMA/BAC	耐候性、黄变性好，丰满度好；和胺族固化剂拼用，在ABS塑料附着力好。可用作ABS塑料一次性施工面漆；Film build, durable, anti-yellowing, compatibility with CAB, adhesion in ABS plastic.	塑胶漆； Plastic coat
U7021	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	光泽高、丰满度好、流平鲜映性好、硬度高； Gloss, good film build, levelling, hardness, distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industrial field
U7025	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~11	2.5%	二甲苯/PMA XYL/PMA	通用树脂；鲜映性、流平性、光泽好； Economy grade, gloss, levelling, durable, distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industrial field
U7030	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	3.0%	二甲苯/PMA XYL/PMA	通用树脂；鲜映性、流平性、光泽好； Economy grade, gloss, levelling, durable, distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industrial field
U7032B	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~10	3.2%	醋酸丁酯 BAC	无苯溶剂，光泽高、丰满度好、流平鲜映性好、硬度高； Benzene-free, gloss, good film build, levelling, hardness, distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industrial field
U7032G	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	光泽高、丰满度好、流平鲜映性好、硬度高； Gloss, good film build, levelling, hardness, distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industrial field
U7032H	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	光泽高、流平鲜映性好、硬度高； Gloss, levelling, hardness, distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industrial field
U7038	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~11	3.8%	二甲苯/PMA XYL/PMA	耐乙醇汽油性能好，耐溶剂好，光泽高、硬度高； Ethanol gasoline resistance and solvent, gloss, levelling, hardness	汽车、轿车、和摩托车的面漆和清漆； Topcoat or clear coat for car and motorcycle
U7066	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~11	3.2%	二甲苯/PMA XYL/PMA	E-10改性，丰满度、鲜映性等性能良好； Good build, gloss, levelling, distinctness of image is good	适用于工程车、机床设备等面漆和罩光； Topcoat or clearcoat for industrial field
U7069	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	8~11	3.0%	二甲苯/PMA XYL/PMA	耐候性、丰满度、柔韧性特优； Durable, good build, good flexible	汽车、轿车、和摩托车的面漆和清漆； Topcoat or clearcoat for car and motorcycle
U7070	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	4.3%	醋酸丁酯 BAC	无苯溶剂，硬度高，耐溶剂及乙醇汽油好，丰满度、鲜映性、耐候性优越；High OH content, benzene-free, high hardness, solvent resistance, weathering resistance, good drying, levelling, distinctness of image is good	一般工业漆； Industrial coat
U7143	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~11	4.3%	二甲苯/PMA XYL/PMA	高光泽、高丰满度、硬度高；Gloss, good appearance, good build, levelling, hardness	汽车、轿车、和摩托车的面漆和清漆； Topcoat or clearcoat for car and motorcycle
U7543	清澈透明 crystal clear	≤1	75±2	50(Z2)~140(Z5) 3400~9900	5~9	4.3%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐候性、鲜映性等性能优越；High OH content, excellent film build, durable, distinctness of image is good	汽车、轿车、和摩托车的面漆和清漆； Topcoat or clearcoat for car and motorcycle

热固性丙烯酸树脂 Thermosetting acrylic resin

JINBO®

型号 Product	外观 Appearance	色泽 Color (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa·s viscosity (1)Gardner (2)mPa·s(25℃)	酸价 Acidity (mgKOH/g)	溶剂 Solvent	主要性能 Features	主要用途 Main application
K5019	清澈透明 crystal clear	≤1	50±2	9(U)~26(Y) 630~1800	7~11	二甲苯/PM/醋酸丁酯 XYL/PM/BAC	环氧树脂改性，特殊金属底材附着力好； Modification of epoxy resin, adhesion to special metal	金属烘烤底漆； Baking paint for some special metal
K5026	清澈透明 crystal clear	≤1	50±2	16(W)~40(Z1) 1100~2700	5~8	甲苯/二甲苯 TOL/XYL	硬度高，冲击好； Hardness, impact resistance	铝粉烤漆、哑光烤漆； Industrial aluminium and matt baking paint
K5038	清澈透明 crystal clear	≤1	50±2	26(Y)~68(Z3) 1800~4600	5~8	二甲苯 XYL	漆膜干燥快、硬度高，耐冲击和化学品性能好； Good hardness, fast drying, impact and chemical resistance	通用烤漆； General baking painting
K5585	清澈透明 crystal clear	≤1	55±2	9(U)~26(Y) 630~1800	6~10	二甲苯/丁醇 XYL/NBA	颜料润湿性好、与CAB及各类型树脂相容性好； Adhesion, pigment wetting and dispersion, compatibility with CAB	用于汽车底色漆、通用色浆； OEM car color primer, universal masterbatch
K6019	清澈透明 crystal clear	≤1	60±2	50(Z2)~140(Z5) 3400~9900	3~6	二甲苯/异丁醇/100# XYL/IBA/S-100	铝粉定向佳，储存稳定性好； Aluminium orientation, general performance	通用烤漆； General baking painting
K6020	清澈透明 crystal clear	≤1	60±2	19(X)~50(Z2) 1300~3400	5~9	二甲苯 XYL	综合性能好； General performance	通用烤漆； General baking painting
K6050	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	60~90	二甲苯/丁醇/乙二醇丁醚 XYL/NBA/BCS	硬度高，对玻璃铜、铝合金、不锈钢等附着力良好； Good hardness, adhesion to glass, aluminium alloy and stainless steel	玻璃、铝合金、不锈钢烤漆； Baking paint for glass, aluminium alloy and stainless
K6053	清澈透明 crystal clear	≤1	60±2	19(X)~50(Z2) 1300~3400	20~30	二甲苯/丁醇/乙二醇乙醚 XYL/NBA/ECS	硬度高，对玻璃铜、铝合金、不锈钢等附着力良好； Good hardness, adhesion to glass, aluminium alloy and stainless steel	玻璃、铝合金、不锈钢烤漆； Baking paint for glass, aluminium alloy and stainless
K6060	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	3~6	二甲苯/醋酸丁酯 XYL/BAC	铝粉定向性优，与环氧、CAB相容； Aluminium orientation, good compatibility with CAB and epoxy resin	金属闪光漆，车辆表面涂装、家用电器涂装； Car and industrial aluminium baking paint
K6061	清澈透明 crystal clear	≤1	60±2	16(W)~40(Z1) 1100~2700	5~9	二甲苯/100# XYL/S-100	光泽高，丰满度好； Gloss, film build	通用烤漆； General baking painting
K6086	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	8~13	二甲苯/丁醇 XYL/NBA	附着力好，颜料润湿性好； Adhesion, pigment wetting and dispersion	OEM 汽车底漆； OEM car primer
K6466	清澈透明 crystal clear	≤1	64±2	50(Z2)~140(Z5) 3400~9900	8~12	丁醇/100# NBA/S-100	耐擦洗及耐水性好，耐溶剂和耐刮性好； Resistance to scratch, water, solvent and washing	汽车原厂色漆及烘烤型工业面漆； OEM car topcoat for car and industrial
K6510	清澈透明 crystal clear	≤1	65±2	19(X)~50(Z2) 1300~3400	4~8	二甲苯/100# XYL/S-100	光泽高，耐汽油和耐盐雾性能优异； Gloss, oil resistance and salt spray resistance	通用烤漆； General baking painting
K6526	清澈透明 crystal clear	≤1	65±2	34(Z)~91(Z4) 2300~6200	5~9	二甲苯/醋酸丁酯/仲丁酯 XYL/BAC/SBAC	综合性能好； General performance	通用烤漆； General baking painting

热固性丙烯酸树脂 Thermosetting acrylic resin

型号 Product	外观 Appearance	色 泽 Color (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa · s viscosity (1)Gardner (2)mpa · s(25°C)	酸价 Acidity (mgKOH/g)	溶 剂 Solvent	主要性能 Features	主要用途 Main application
K6534	清澈透明 crystal clear	≤1	65±2	26(Y)~68(Z3) 1800~4600	8~13	二甲苯 XYL	附着力好, 耐溶剂性好; Adhesion, solvent resistance	制罐、白可丁及一般工业面漆; Canning and industrial baking painting
K7010A	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	4~8	二甲苯 XYL	综合性能好; General performance	通用烤漆; General baking painting
K7017	清澈透明 crystal clear	≤1	70±2	68(Z3)~140(Z5) 4600~9900	6~10	二甲苯/100# XYL/S-100	机械性能好, 光泽和鲜映性优; Good gloss and other comprehensive performance	汽车原厂清漆和色漆及烘烤型工业面漆; OEM topcoat and clearcoat for car and industrial
K7051	清澈透明 crystal clear	≤1	70±2	34(Z)~91(Z4) 2300~6200	6~10	二甲苯/100# XYL/S-100	流平好, 耐溶剂及耐候性优, 机械性能好; Leveling, durable, solvent resistance and good other comprehensive performance	用于汽车原厂清漆和色漆, 也可用于烘烤型工 业面漆; OEM topcoat and clearcoat for car and industrial
K7057	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	6~10	二甲苯/100# XYL/S-100	层间附着力好, 耐酸及抗老化性能佳; Durable, acid resistance and good other comprehensive performance	汽车原厂清漆和色漆及烘烤型工业面漆; OEM topcoat and clearcoat for car and industrial
K7088	清澈透明 crystal clear	≤1	70±2	34(Z)~91(Z4) 2300~6200	6~11	二甲苯/PMA XYL/PMA	丰满度好, 光泽高; Film build, gloss	汽车原厂清漆和色漆及烘烤型工业面漆; OEM topcoat and clearcoat for car and industrial
K7595	清澈透明 crystal clear	≤1	75±2	68(Z3)~140(Z5) 4600~9900	6~11	二甲苯/100# XYL/S-100	耐候性优, 施工固体份高, 机械性能好; Durable, good film build, comprehensive	用于汽车原厂面漆, 也可用于烘烤型工业面漆; OEM topcoat for car and industrial

热塑性丙烯酸树脂 Thermoplastic acrylic resin

型号 Product	外 观 Appearance	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa · s viscosity (1)Gardner (2)mpa · s(25°C)	酸价 Acidity (mgKOH/g)	Tg (°C)	溶 剂 Solvent	主要性能 Features	主要用途 Main application
P4901	清澈透明 crystal clear	49±2	16(W)~40(Z1) 1100~2700	4~7	60	甲苯 TOL	快干, 附着力好, 硬度高; Fast drying, hardness, good adhesion to metal	气雾漆、防腐漆; Self spray paint, anticorrosive paint
P5002	清澈透明 crystal clear	50±2	26(Y)~68(Z3) 1800~4600	2~5	50	甲苯/醋酸丁酯 TOL/BAC	CAB相溶性好, 铝粉定位佳, 配套性好; Compatibility with CAB, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	塑胶漆, 汽车修补漆1K树脂; Plastic coat, 1K resin for automotive refinish
P5005	清澈透明 crystal clear	50±2	9(U)~26(Y) 630~1800	8~11	40	甲苯/丁酯/异丁醇 TOL/BAC/IBA	环氧改性树脂, 金属底材附着力好; Modification of epoxy resin, good adhesion to metal	防腐漆; Anticorrosive coat
P5018	清澈透明 crystal clear	50±2	16(W)~40(Z1) 1100~2700	2~5	40	甲苯/醋酸丁酯 TOL/BAC	CAB互溶, 铝粉定位性好, 双组份配套性好; Compatibility with CAB, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	塑胶漆; Plastic coat

热塑性丙烯酸树脂 Thermoplastic acrylic resin

JINBO®

型号 Product	外 观 Appearance	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa · s viscosity (1)Gardner (2)mpa · s(25°C)	酸价 Acidity (mgKOH/g)	Tg (°C)	溶 剂 Solvent	主要性能 Features	主要用途 Main application
P5022	清澈透明 crystal clear	50±2	16(W)~40(Z1) 1100~2700	2~5	78	甲苯/醋酸丁酯 TOL/BAC	干性快、硬度高, 和硝化棉互溶。在ABS、PS、HIPS等 塑料底材附着力好; Compatibility with NC, hardness, adhesion to ABS, PS, PS, HIPS plastic	塑胶漆; Plastic coat
P5029	清澈透明 crystal clear	50±2	16(W)~40(Z1) 1100~2700	7~12	29	甲苯 TOL	综合性能好; General performance	道路漆、标志漆; Road paint, mark paint
P5035	清澈透明 crystal clear	50±2	50(Z2)~140(Z5) 3400~9900	5~8	90	甲苯/醋酸丁酯 TOL/BAC	干性快、硬度高、铝粉漆效果好, 在ABS塑料上有良好的 附着力, 和双组份面漆的配套性好; Hardness, aluminium orientation, adhesion in ABS plastic, inter-layer adhesion with top PU coat	塑胶漆; Plastic coat
P5036	清澈透明 crystal clear	50±2	9(U)~26(Y) 630~1800	5~10	38	二甲苯/醋酸丁酯 XYL/BAC	耐候性好, 附着力好; Durable, good adhesion	彩瓦漆; Color coat of tile
P5050	清澈透明 crystal clear	50±2	16(W)~40(Z1) 1100~2700	8~12	40	甲苯/醋酸丁酯 TOL/BAC	可与硝化棉互溶, ABS塑料附着力好, 和双组份配套性好; Compatibility with NC, adhesion to ABS plastic, inter-layer adhesion with top PU coat	塑胶漆; Plastic coat
P5066	清澈透明 crystal clear	50±2	91(Z4)~220(Z6) 6200~15000	3~5	66	甲苯/异丁醇 TOL/IBA	在ABS塑料上附着力好, UV罩光后耐沸水性能好; Boiling water resistance, adhesion to ABS plastic, inter-layer adhesion with top PU/UV coat	UV塑胶底漆; Plastic coat
P5068	清澈透明 crystal clear	50±2	50(Z2)~140(Z5) 3400~9900	5~8	86	甲苯/醋酸丁酯 TOL/BAC	高耐醇性树脂, 与硝化棉互溶; Compatibility with NC, alcohol resistance, adhesion to ABS and PVC plastic	ABS塑料漆, PVC油漆; Plastic coat
P5080	清澈透明 crystal clear	50±2	34(Z)~91(Z4) 2300~6200	4~8	55	二甲苯/100# XYL/S-100	耐候性, 耐酸、耐碱、耐水性能好; Durable, water resistance, chemical resistance	外墙底漆、面漆, 防腐面漆; Primer and topcoat of exterior wall, anti-corrosive topcoat
P5086	清澈透明 crystal clear	50±2	16(W)~40(Z1) 1100~2700	7~11	20	二甲苯 XYL	柔韧性好, 在马口铁、冷轧板等底材附着力好; Good flexible, good adhesion to metal	金属底、面漆; Primer and topcoat of metal
P5090	清澈透明 crystal clear	50±2	91(Z4)~220(Z6) 6200~15000	1~4	92	甲苯/丁酯/异丁醇 TOL/BAC/IBA	ABS附着力好, 硬度高, 防掉银、耐酒精擦; Good hardness, anti-aluminium drop, alcohol rub resistance, adhesion to ABS plastic	塑胶漆; Plastic coat
P5093	清澈透明 crystal clear	50±2	16(W)~40(Z1) 1100~2700	5~9	58	甲苯/醋酸丁酯 TOL/BAC	干性快、硬度高, 丰满度好; Fast drying, hardness, film build	机器、机床、车辆的面漆; Topcoat of metal
P5103	清澈透明 crystal clear	50±2	19(X)~50(Z2) 1300~3400	2~5	60	甲苯/异丁醇 TOL/IBA	醇溶, CAB、NC互溶, ABS、PS、HIPS附着力好; Dissolved in alcohol, compatibility with CAB&NC, adhesion to ABS,PS,PS,HIPS plastic	用于易咬底的塑料底材; Plastic coat
P5112	清澈透明 crystal clear	50±2	16(W)~40(Z1) 1100~2700	3~6	40	二甲苯/PMA XYL/PMA	耐候性好, 颜料分散性好, CAB互溶, 铝粉定位性好, 双组 份配套性好; Compatibility with CAB, pigment wetting and dispersion, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	塑胶漆, 汽车修补漆1K色母树脂; Plastic coat, 1K masterbatch of automotive refinish
P6006	清澈透明 crystal clear	60±2	19(X)~50(Z2) 1300~3400	8~12	25	甲苯/醋酸丁酯 TOL/BAC	与氯化橡胶互溶, 耐候性好, 柔韧性好; Compatibility with chlorinated rubber, durable, film-build	防腐漆; Anticorrosive coat

聚丙烯PP塑料专用树脂 Thermoplastic resin for polypropylene plastic coat

金博树脂

型号 Product	外观 Appearance	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa·s viscosity (1)Gardner (2)mpa·s(25°C)	酸价 Acidity (mgKOH/g)	Tg (°C)	溶剂 Solvent	主要性能 Features	主要用途 Main application
PP-04B	混浊、微黄 Slight yellow, not clear	40±2	5~20 400~1800	3~6	93	甲苯 TOL	PP件底漆，各色面漆，硬度比PP-03B高（汽车内饰件油漆）；Adhesion to PP plastic, hardness, water resistance, compatibility with NC	PP塑料漆 PP coat
PP-08	混浊、微黄 Slight yellow, not clear	45±2	9(U)~26(Y) 630~1800	2~5	50	醋酸乙酯/醋酸丁酯 EAC/BAC	无苯环保型，PP底材上附着力好，综合性能优； Benzene free, adhesion to PP plastic, hardness, water resistance	PP塑料漆 PP coat
PP-10A	混浊、微黄 Slight yellow, not clear	45±2	9(U)~26(Y) 630~1800	2~5	60	甲苯/MIBK TOL/MIBK	PP件底漆，各色面漆，金属漆，耐水性能佳，配套附着力好（耐沸水4小时、耐水240小时），施工性能好； Adhesion to PP plastic, excellent water and boiling water resistance, compatibility with CAB, aluminium orientation	PP塑料漆 PP coat
PP-13A	混浊、微黄 Slight yellow, not clear	45±2	9(U)~26(Y) 630~1800	2~5	45	甲苯 TOL	PP件底漆，各色面漆； Adhesion to PP plastic, water resistance	PP塑料漆 PP coat
PP-13B	混浊、微黄 Slight yellow, not clear	40±2	9(U)~26(Y) 630~1800	2~5	45	甲苯/MIBK TOL/MIBK	PP件底漆，各色面漆，金属漆； Adhesion to PP plastic, water resistance, compatibility with CAB, aluminium orientation	PP塑料漆 PP coat
PP-15	混浊、微黄 Slight yellow, not clear	40±2	5~20 400~1800	3~6	75	甲苯 TOL	PP件底漆，各色面漆（耐沸水2小时）； Adhesion to PP plastic, hardness, good water resistance	PP塑料漆 PP coat

汽车修补漆树脂 Acrylic resin for automotive refinish

型号 Product	外观 Appearance	色 泽 Color (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa·s viscosity (1)Gardner (2)mpa·s(25°C)	酸价 Acidity (mgKOH/g)	羟基含量 OH content (100%)	溶剂 Solvent	主要性能 Features	主要用途 Main application
K1-01	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5		甲苯/醋酸丁酯 TOL/BAC	CAB相溶性好，铝粉定位佳，配套性好； Compatibility with CAB, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	1K树脂 1K resin
K1-02	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5		甲苯/醋酸丁酯 TOL/BAC	CAB互溶，铝粉定位性好，双组份配套性好； Compatibility with CAB, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	1K树脂 1K resin
K1-03	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5		二甲苯/PMA XYL/PMA	耐候性好，颜料分散性好，CAB互溶，铝粉定位性好，双组份配套性好； Compatibility with CAB, pigment wetting and dispersion, aluminium orientation, adhesion to ABS plastic, inter-layer adhesion with top PU coat	1K树脂 1K resin
K2-01	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	5~9	2.6%	二甲苯/PMA XYL/PMA	颜料润湿及分散性好，耐候性佳、和CAB相溶性好； Pigment wetting, compatibility with CAB, durable, yellowing resistance	1K/2K 通用树脂 1K/2K universal resin
K2-02	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	5~9	2.7%	二甲苯/PMA XYL/PMA	颜料润湿及分散性； Pigment wetting, general performance	2K树脂 2K resin
K2-03	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	5~9	3.4%	二甲苯/PMA XYL/PMA	颜料润湿及分散性； Pigment wetting, general performance	2K树脂 2K resin
TA-01	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐黄变性、耐候性、干性、流平性等性能优越； Huge solid, good film build, gross, durable, yellowing resistance, good drying, levelling, good appearance	清漆 Clearcoat
TA-02	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	4.2%	二甲苯/PMA XYL/PMA	硬度高、鲜映性、光泽、耐候性、耐黄变性、流平性优越； High OH content, hardness, built, weathering resistance, yellowing resistance, good drying, levelling	清漆 Clearcoat
TC-01	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~11	2.5%	二甲苯/PMA XYL/PMA	通用树脂；鲜映性、流平性、光泽好； Economy grade,gloss, levelling, durable	清漆 Clearcoat
TC-02	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~11	3.0%	二甲苯/PMA XYL/PMA	通用树脂；鲜映性、流平性、光泽好； Economy grade,gloss, levelling, durable	清漆 Clearcoat
TC-03	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	通用树脂；鲜映性、流平性、光泽好； Economy grade,gloss, levelling, durable	清漆 Clearcoat
TC-04	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	通用树脂；鲜映性、流平性、光泽好； Economy grade,gloss, levelling, durable	清漆 Clearcoat
TK-01	清澈透明 crystal clear	≤1	70±2	68(Z3)~140(Z5) 4600~9900	5~9	3.0%	二甲苯/醋酸丁酯 XYL/BAC	快干、耐黄变性、耐候性、干性、流平性等性能优越； Fast drying, durable, yellowing resistance, levelling	清漆 Clearcoat
TK-02	清澈透明 crystal clear	≤1	70±2	68(Z3)~140(Z5) 4600~9900	6~11	4.0%	二甲苯/醋酸丁酯 XYL/BAC	快干、耐黄变性、耐候性、干性、流平性等性能优越； Fast drying, durable, yellowing resistance, levelling	清漆 Clearcoat