羟基丙烯酸树脂 Hydroxyl acrylic resin

金博树脂

型 号 Product	外 观 Appearance	色 泽 Color (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa · s vicosity (1)Gardner (2)mpa · s(25℃)	酸价 Acidity (mgKOH/g)	羟基含量 OH content (100%)	溶 剂 Solvent	主要性能 Features	主要用途 Main application
U3018	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	二甲苯/PMA XYL/PMA	丰满度、耐黄变性、耐候性、干性、流平性等性能优越； Good film build, gross, durable, yellowing resistance, drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clearcoat for car
U3025	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐黄变性、耐候性、干性、流平性等性能优越； Good film build, durable, yellowing resistance, good drying，levelling	汽车、轿车面漆、清漆； Topcoat or clearcoat for car
U3025B	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	醋酸丁酯 BAC	无苯溶剂，丰满度、耐黄变性、耐候性、干性等性能优越； Benzene-free, film build, durable, yellowing resistance, drying, levelling	汽车、轿车面漆、清漆； Topcoat or clearcoat for car
U3040	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐黄变性、耐候性、干性、流平性等性能优越，经济型；Film build, durable, yellowing resistance, drying, levelling, economy grade	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive repair, anticorrosive and industral field
U3060	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	耐黄变性、耐候性、干性、流平性等性能优越，经济型； Durable, yellowing resistance, drying, levelling, economy grade	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive repair, anticorrosive and industral field
U3090K	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	5~9	3.0%	二甲苯/醋酸丁酯 XYL/BAC	快干、耐黄变性、耐候性、干性、流平性等性能优越； Fast drying，durable，yellowing resistance，levelling	汽车快修清漆； Fast drying clearcoat for automotive refinish
U3125	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	3.2%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐黄变性、耐候性、鲜映性等性能优越； Film built, weathering resistance, yellowing resistance, good drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clearcoat for car
U4025A	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	4.3%	二甲苯/PMA XYL/PMA	高羟基、丰满度、耐侯性、耐黄变、干性优越； High OH content, film built, weathering resistance, yellowing resistance, good drying, levelling	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4025C	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	5~9	4.3%	二甲苯/PMA XYL/PMA	丰满度、硬度、耐侯性、耐黄变、干性优越； High OH content, film build, weathering resistance, yellowing resistance, drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4035	清澈透明 crystal clear	≤1	70±2	34(Z)~91(Z4) 2300~6200	5~9	4.3%	醋酸丁酯 BAC	无苯溶剂，丰满度、耐侯性、耐黄变、干性优越； Benzene-free, high OH content, Film build, weathering resistance, yellowing resistance, drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4040	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	4.3%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐侯性、耐黄变优越，性价比高； High OH content, Film build, weathering resistance, yellowing resistance, drying, economic grade	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4060	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	5~9	4.3%	二甲苯/醋酸丁酯 XYL/BAC	耐侯性、耐黄变性优越，性价比高； High OH content, weathering resistance, yellowing resistance, drying, economic grade	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆； Topcoat or clearcoat for car, automotive refinish anticorrosive and industral field
U4090K	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	6~11	4.0%	二甲苯/醋酸丁酯 XYL/BAC	快干、耐黄变性、耐侯性、干性、流平性等性能优越； Fast drying, durable, yellowing resistance, levelling	汽车快修清漆； Fast drying clearcoat for automotive repair
U4240	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	4.3%	二甲苯/PMA XYL/PMA	硬度高、鲜映性、光泽、耐侯性、耐黄变性、流平性优越； High OH content, hardness, built, weathering resistance, yellowing resistance, drying, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clear coat for car
U4543	清澈透明 crystal clear	≤1	75±2	50(Z2)~140(Z5) 3400~9900	5~9	4.3%	二甲苯/PMA XYL/PMA	丰满度、耐黄变性、耐侯性、鲜映性等性能优越；High OH content, good film built, weathering resistance, yellowing resistance, levelling, distinctness of image is good	汽车、轿车面漆、清漆； Topcoat or clear coat for car

羟基丙烯酸树脂 Hydroxyl acrylic resin

JINBO®

型 号 Product	外 观 Appearance	色 泽 Color (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa·s vicosity (1)Gardner (2)mpa·s(25℃)	酸价 Acidity (mgKOH/g)	羟基含量 OH content (100%)	溶 剂 Solvent	主要性能 Features	主要用途 Main application
U5003	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	甲苯/醋酸丁酯 TOL/BAC	耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Good alcohol resistance, compatibility with CAB381, aluminium orientation, adhesion in ABS plastic, inter-layer adhesion with top clear.	塑胶漆； Plastic coat
U5003B	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	醋酸丁酯 BAC	无苯溶剂，耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Benzene-free, good alcohol resistance, compatibility with CAB381, aluminium orientation, adhesion in ABS plastic, inter-layer adhesion with top clear.	塑胶漆； Plastic coat
U5018	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	甲苯/醋酸丁酯 TOL/BAC	耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Good alcohol resistance, compatibility with CAB381, aluminium orientation, weathering resistance, yellowing resistance, adhesion in ABS plastic, inter-layer adhesion with top PU clear coating.	塑胶漆； Plastic coat
U5020	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	醋酸丁酯/醋酸仲丁酯 BAC/SBAC	无苯溶剂，耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Benzene-free, good alcohol resistance, compatibility with CAB381, aluminium orientation, weathering resistance, yellowing resistance, adhesion in ABS plastic, inter-layer adhesion to top PU&UV clear coating.	塑胶漆； Plastic coat
U5020A	清澈透明 crystal clear	≤1	50±2	19(X)~50(Z2) 1300~3400	2~5	2.0%	二甲苯/醋酸丁酯 XYL/BAC	耐醇性好，和CAB互溶，铝粉排列优，ABS塑料、马口铁板附着力好，双-双-双配套性好；Good alcohol resistance，compatibility with CAB381，aluminium orientation，weathering resistance，yellowing resistance，adhesion in ABS plastic，inter-layer adhesion to top PU&UV clear coating.	塑胶漆； Plastic coat
U5112	清澈透明 crystal clear	≤1	50±2	16(W)~40(Z1) 1100~2700	2~5	1.8%	二甲苯/PMA XYL/PMA	低气味，与CAB互溶，铝粉定位性好，耐候性好；Low odor，compatibility with CAB，aluminium orientation，adhesion in ABS plastic，inter-layer adhesion with top PU&UV clear coating.	塑胶漆、外墙漆； Plastic coat, exterior wall coat
U6020	清澈透明 crystal clear	≤1	60±2	19(X)~50(Z2) 1300~3400	5~9	2.8%	二甲苯 XYL	通用PU树脂； Standard for industral coating. Economy grade	工业漆； Industral coat
U6025	清澈透明 crystal clear	≤1	60±2	16(W)~40(Z1) 1100~2700	4~8	2.1%	二甲苯/醋酸丁酯 XYL/BAC	和CAB381-0.5 混溶性好，附着力好，耐候性优，铝粉定位性好；Compatibility with CAB，durable，non yellowing	汽车中涂、底漆、一般工业漆； Primer for car and industral field
U6026A	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	5~9	2.6%	二甲苯/PMA XYL/PMA	颜料润湿及分散性好，耐候性佳、和CAB相溶性好；Pigment wetting，compatibility with CAB，durable，yellowing resistance	汽车修补1K/2K通用色母，汽车面漆；1K/2K solid color for automotive refinish
U6027	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	5~9	2.7%	二甲苯/PMA XYL/PMA	颜料润湿及分散性； Pigment wetting, general performance	修补漆2K通用色母； 2K solid color for automotive refinish
U6028	清澈透明 crystal clear	≤1	60±2	91(Z4)~220(Z6) 6200~15000	6~11	2.8%	二甲苯/醋酸丁酯 XYL/BAC	在金属底材上附着力好，耐原子灰中的苯乙烯溶解；Adhesion to metal，resistanc to styrene in putty	需要快速批刮原子灰的金属底漆；Metal primer on which putty is needed to cover in short time
U6034	清澈透明 crystal clear	≤1	60±2	9(U)~26(Y) 630~1800	5~9	3.4%	二甲苯/PMA XYL/PMA	颜料润湿及分散性； Pigment wetting，general performance	修补漆2K通用色母； 2K solid color for automotive refinish
U6040	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	5~9	2.6%	二甲苯/PMA/100# XYL/PMA/S-100	耐侯性、耐酸碱、耐溶剂、耐水； Durable，chemical resistance	工程防腐、工业等面漆； Anticorrosive and industral coat
U6045	清澈透明 crystal clear	≤1	60±2	19(X)~50(Z2) 1300~3400	5~9	2.8%	二甲苯/PMA/100# XYL/PMA/S-100	光泽、耐侯性、流平性、鲜映性好；Gloss，durable，leveling，distinctness of image is good	汽车面漆；Solid color topcoat for automobile
U6063	清澈透明 crystal clear	≤1	60±2	34(Z)~91(Z4) 2300~6200	2~5	1.8%	甲苯/醋酸丁酯 TOL/BAC	耐醇性好，和CAB互溶，铝粉定位性好，适用于塑料一道面漆；Good alcohol resistance, compatibility with CAB，aluminium orientation, weathering resistance, yellowing resistance, adhesion in ABS plastic	塑胶漆 Plastic coat

羟基丙烯酸树脂 Hydroxyl acrylic resin

金博树脂

型 号 Product	外 观 Appearance	色 泽 Color (Fe-Co)	固体份 Non-volatile matter (%)	粘度(1)格式管, s; (2)标准粘度, mPa·s vicosity (1)Gardner (2)mpa·s(25℃)	酸价 Acidity (mgKOH/g)	羟基含量 OH content (100%)	溶 剂 Solvent	主要性能 Features	主要用途 Main application
U6526	清澈透明 crystal clear	≤1	65±2	34(Z)~91(Z4) 2300~6200	5~9	2.6%	二甲苯/醋酸丁酯/仲丁酯 XYL/BAC/SBAC	通用树脂；性价比高、综合性能良好； Standard for industral coating，Economy grade for PU resin	可用于防腐、工程机械、机床设备、地坪领域等面漆； Coat for anticorrosive, industral and floor field
U7010A	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	4~8	2.6%	二甲苯 XYL	通用树脂；性价比高、综合性能良好； Standard for industral coating，Economy grade for PU resin	一般工业漆； Industral coat
U7012A	清澈透明 crystal clear	≤1	70±2	91(Z4)~220(Z6) 6200~15000	4~8	2.4%	二甲苯/PMA/醋酸丁酯 XYL/PMA/BAC	耐候性、黄变性好，丰满度好；和肪族固化剂拼用，在ABS塑料附着力好。可用作ABS塑料一次性施工面漆；Film build，durable，anti-yellowing，compatibility with CAB，adhesion in ABS plastic.	塑胶漆； Plastic coat
U7021	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	光泽高、丰满度好、流平鲜映性好、硬度高； Gloss, good film build, levelling, hardness，distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industral field
U7025	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~11	2.5%	二甲苯/PMA XYL/PMA	通用树脂；鲜映性、流平性、光泽好； Economy grade, gloss，levelling，durable，distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industral field
U7030	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	3.0%	二甲苯/PMA XYL/PMA	通用树脂；鲜映性、流平性、光泽好； Economy grade, gloss，levelling，durable，distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industral field
U7032B	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~10	3.2%	醋酸丁酯 BAC	无苯溶剂，光泽高、丰满度好、流平鲜映性好、硬度高； Benzene-free, gloss, good film build, levelling, hardness，distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industral field
U7032G	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	光泽高、丰满度好、流平鲜映性好、硬度高； Gloss, good film build, levelling, hardness，distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industral field
U7032H	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~10	3.2%	二甲苯/醋酸丁酯 XYL/BAC	光泽高、流平鲜映性好、硬度高； Gloss，levelling，hardness，distinctness of image is good	汽车、轿车、防腐、修车修补、各类机床等面漆、清漆；Topcoat or clearcoat in car, automotive refinish anticorrosive and industral field
U7038	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~11	3.8%	二甲苯/PMA XYL/PMA	耐乙醇汽油性能好，耐溶剂好，光泽高、硬度高； Ethanol gasoline resistance and solvent，gloss，levelling，hardness	汽车、轿车、和摩托车的面漆和清漆；Topcoat or clear coat for car and motorcycle
U7066	清澈透明 crystal clear	≤1	70±2	50(Z2)~140(Z5) 3400~9900	7~11	3.2%	二甲苯/PMA XYL/PMA	E-10改性，丰满度、鲜映性等性能良好； Good build, gloss, levelling, distinctness of image is good	适用于工程车、机床设备等面漆和罩光；Topcoat or clearcoat for industral field
U7069	清澈透明 crystal clear	≤1	70±2	16(W)~40(Z1) 1100~2700	8~11	3.0%	二甲苯/PMA XYL/PMA	耐侯性、丰满度、柔韧性特优； Durable，good build，good flexible	汽车、轿车、和摩托车的面漆和清漆；Topcoat or clearcoat for car and motorcycle
U7070	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	5~9	4.3%	醋酸丁酯 BAC	无苯溶剂，硬度高，耐溶剂及乙醇汽油好，丰满度、鲜映性、耐候性优越；High OH content，benzene-free，high hardness，solvent resistance，weathering resistance，good drying，levelling，distinctness of image is good	一般工业漆； Industral coat
U7143	清澈透明 crystal clear	≤1	70±2	26(Y)~68(Z3) 1800~4600	7~11	4.3%	二甲苯/PMA XYL/PMA	高光泽、高丰满度、硬度高；Gloss，good appearance，good build，levelling，hardness	汽车、轿车、和摩托车的面漆和清漆；Topcoat or clearcoat for car and motorcycle
U7543	清澈透明 crystal clear	≤1	75±2	50(Z2)~140(Z5) 3400~9900	5~9	4.3%	二甲苯/醋酸丁酯 XYL/BAC	丰满度、耐候性、鲜映性等性能优越；High OH content，excellent film build, durable, distinctness of image is good	汽车、轿车、和摩托车的面漆和清漆；Topcoat or clearcoat for car and motorcycle